

ABS

**Features** Medium flow, Recycled raw material

Property	Value	Unit	Test method
<b>PHYSICAL PROPERTIES</b>			
Density	1,05	g/cm <sup>3</sup>	ISO 1183
MFI at 230°C/5 kg	8	g/10 min	ISO 1133
<b>MECHANICAL PROPERTIES</b>			
Flexural modulus at +23°C	2100	MPa	ISO 178
Maximum flexural strength	70	MPa	ISO 178
Maximum tensile strength	35	MPa	ISO 527-2
<b>IMPACT PROPERTIES</b>			
Notched Charpy at +23°C	10	kJ/m <sup>2</sup>	ISO 179
Notched Charpy at -20°C	--	kJ/m <sup>2</sup>	ISO 179
<b>THERMAL PROPERTIES</b>			
Vicat 50°C/h at 49,05N (B)	95	°C	ISO 306
<b>FLAMMABILITY PROPERTIES</b>			
UL94 at 1.6 mm	HB	--	UL94
<b>ADDITIONAL INFORMATION</b>			
Mould shrinkage (with flow)	0,6 - 0,8	%	Polykemi
Mould shrinkage (across flow)	0,6 - 0,8	%	Polykemi
<b>PROCESS INSTRUCTIONS</b>			
Drying time	2-4	h	--
Drying temperature	70-80	°C	--
Melt temperature	200-240	°C	--
Mould temperature	60-80	°C	--
Peripheral screw speed	400-600	mm/s	--
Back pressure	60-100	bar	--

Further material information is available upon request

Stated values in this datasheet are approximate. The values originate, if nothing else is stated, from standardized test specimens in natural color. All information, recommendations and advice, written or verbal, given by an individual company within, or agent affiliated with, The Polykemi Group are according to our knowledge to the date of this edition, correct and given in good faith. It is the responsibility of the customer to test and evaluate if the material suits the application and the environment in which it is intended to be used. Companies within, or agent affiliated with, The Polykemi Group can not be held responsible or liable for any loss incurred through incorrect or faulty use of the products. When producing details in flame retardant material, corrosion protected steel is to recommend for the mould. We takes no responsibility for any printing errors.

Visiting address  
Bronsgatan 8  
SE-271 39 YSTAD

+46 (0)411 170 30  
rondo@rondoplast.se  
www.rondoplast.se

THE POLYKEMI GROUP  
**polykemi**   
**rondo**  **scanfill** 

Version 1 2020-11-09